ACRYFLEX-T · TENNIS COURT SYSTEM

Acrylic Resurfacer 367-43

Ready-to-use pure acrylic based resurfacer

COLOUR
Black

1.55 g/cm³	68 %	20 min	2 h	0.600 kg/m²
Specific gravity (approx.)	Solids content (wt.)	Touch dry	Time between coats	Theor. consumption

Product description

ACRYLIC RESURFACER 367-43 is a 100 % pure acrylic based filler and levelling material that already contains suitably selected silica texture. It fills gaps in concrete or asphalt sub-structures, hides aggregate profiles and smoothens the surface.

Product characteristics

- 100 % pure acrylic based filler / levelling material with silica sand content.
- Fills gaps in concrete or asphalt sub-structures and hides aggregate profiles.
- Smoothens concrete or asphalt sub-structures.

Advantages

- Hard and highly wear-resistant
- Ready-to-use product
- Easy mixing on the field
- Easy application
- High adhesion
- Dries quickly
- Cost-effective

Position in the system

- **Finishing** — OVERLINE 367-F lines · GLOSSCOAT sealer
- **Colour coat** — PRECOAT 367-200 range
- **Cushion layers** — UNIRUBBER range
- **Resurfacer** — ACRYLIC RESURFACER 367-43 — THIS PRODUCT
- **Primer** — ACRYLIC PRIMER 367-28 · AQ PRIMER 2K
- **Sub-base** — Asphalt / concrete

ACRYFLEX-T

Cushioned acrylic tennis court system

ITF classified system surfaces

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Technical data (at +20 °C)

Colour	**Black**	Time between coats	**2 hours**
Specific gravity (approx.)	**1.55 g/cm³**	Theoretical consumption	**0.600 kg/m² (1 coat)**
Solids content (by weight)	**68 %**	Application temperature	**+14 °C to +35 °C**
Touch dry	**20 minutes**	Shelf life	**12 months**

Application procedure

01

Surface preparation

Clean the surface of oil, dirt, mortar residues, dust and other contaminants.

02

Mixing

Contains selected silica texture. If necessary add up to 5 % tap water* and mix with a slow-speed mixer until homogeneous.

03

Application

Apply with a rubber squeegee at a theoretical rate of 0.600 kg/m² per coat.

Application conditions

+14 °C – +35 °C

Do not apply the material at temperatures below +14 °C or above +35 °C.

Consumption

0.600 kg/m²

Theoretical consumption per coat, depending on surface permeability and porosity.

Important: consumption may vary depending on surface roughness, ambient temperature and application technique. Values were determined under laboratory conditions on concrete / wearing-course asphalt at the recommended mixing ratios. *In hot weather up to 5 % more water may be added.

Packaging

- 20 kg plastic buckets
- 60 kg plastic barrels

Storage

- Store in the unopened original packaging in closed, dry storage areas at +15 °C to +35 °C.
- Shelf life: 12 months from the date of manufacture in a cool, dry place.
- Do not expose to sunlight outdoors.
- Protect from freezing in cold weather.

Safety

- Not classified as hazardous.
- Contains no formaldehyde, asbestos, mercury, lead, chromate or their derivatives.
- Contains fire-retardant additives.
- For safe handling and occupational health & safety see the Safety Data Sheet (SDS).

LEGAL NOTE

The explanations provided in this technical data sheet are based on test evaluations and results conducted according to relevant standards and are intended to guide applicators. As workmanship, weather conditions, construction, equipment used and other variables that may affect results are entirely beyond our control, UNICA does not provide any explicit or implicit warranty regarding this material. UNICA only guarantees that the material conforms to its product specifications, and its sole responsibility towards the buyer or user of this product is limited to the replacement value of the product in case of manufacturing defects. Under no circumstances shall UNICA be liable for any direct or incidental, special or consequential injury, loss or damage arising from the material or its application. UNICA shall not be held responsible in any way for any defects, alterations or changes in conditions in the substrate where its products are applied.