ACRYFLEX-T · TENNIS COURT SYSTEM

Acrylic Resurfacer LW 367-30

Light weight acrylic latex based resurfacer

COLOUR
Black

0.78 g/cm³	36 %	1–1½ h	min. 3 h	0.250–0.300 kg/m²
Density (approx.)	Solids content (wt.)	Touch dry	Overcoating interval	Theor. consumption

Product description

ACRYLIC RESURFACER LW 367-30 is a 100 % acrylic latex based light weight filling coat, blended on site with silica sand and water. It is applied before **PRECOAT 367-200**, **PRECOAT 367-43**, **PAVERCOAT 43 2K** and **UNIRUBBER** layers of **ACRYFLEX-T** tennis courts and cycle path systems.

Product characteristics

- Thanks to the specific elastic microspheres it contains, it has low density and high resilience.
- Fills voids and hides the profile of aggregates in concrete or asphalt sub-bases.
- Makes the sub-base smoother and increases the yield of subsequent **PRECOAT 367-200**, **PRECOAT 367-43**, **PAVERCOAT 43 2K** or **UNIRUBBER** layers.

Advantages

- Elastic and extremely low density
- Very high resilience
- Low consumption
- Easy mixing on site
- Cost-effective
- Easy application

Position in the system

Finishing
OVERLINE 367-F lines · GLOSSCOAT sealer

Colour coat
PRECOAT 367-200 range

Cushion layers
UNIRUBBER range

Resurfacer
ACRYLIC RESURFACER LW 367-30 — THIS PRODUCT

Primer
ACRYLIC PRIMER 367-28 · AQ PRIMER 2K

Sub-base
Asphalt / concrete

ACRYFLEX-T

Cushioned acrylic tennis court system

ITF classified system surfaces

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Technical data (at +20 °C)

Colour	**Black**	Overcoating interval	**minimum 3 h**
Mass density (approx.)	**0.78 g/cm³**	Theoretical consumption	**0.250–0.300 kg/m² (1 layer, without sand)**
Solids content (by weight)	**36 %**	Application temperature	**+14 °C to +35 °C**
Touch dry	**1–1½ h**	Shelf life	**12 months**

Application procedure

01

Surface preparation

Clean the surface of grease, salts, debris, dust and any other contaminants.

02

Priming

Apply **ACRYLIC RESURFACER LW 367-30** after **ACRYLIC PRIMER 367-28** or **AQ PRIMER 2K**.

03

Mixing

Add suitable grade silica sand or quartz and tap water. Mix with a slow-speed mixer until homogeneous.

04

Application

Spread with a rubber blade squeegee at a theoretical rate of 0.250–0.300 kg/m² per layer.

Mixing ratio (by weight)



- **60 kg** — ACRYLIC RESURFACER LW 367-30
- **40 kg** — Silica sand / quartz (0.1–0.3 mm)
- **10 kg*** — Water*

*The amount of water may vary with ambient temperature. In hot weather up to 5 % more water may be added.

Application conditions
+14 °C – +35 °C
Do not apply the material at temperatures below +14 °C or above +35 °C.

Consumption
0.250–0.300 kg/m²
Theoretical spreading rate per layer, depending on surface permeability and porosity.

Important: coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Packaging

- 50 kg polyethylene drums
- 180 kg steel drums

Storage

- Store in sealed drums in an indoor, dry warehouse at +15 °C to +35 °C.
- Shelf life: 12 months from the production date in a cool, dry place.
- Do not leave the product outdoors exposed to the sun.

Safety

- Not classified as hazardous.
- Contains no formaldehyde, asbestos, mercury, lead, chromate or their derivatives.
- Contains fire-retardant additives.
- For safe handling and occupational health & safety see the Safety Data Sheet (SDS).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.