ACRYFLEX-T · TENNIS COURT SYSTEM

Glosscoat 367-TIX

100 % pure acrylic latex based clear drying protective sealer

FINISH
Clear
ultra matt sealer

0.93 g/cm³	39 %	30 min	min. 2 h	0.150–0.200 kg/m²
Density (approx.)	Solids content (wt.)	Touch dry	Overcoating interval	Theor. consumption

Product description

GLOSSCOAT 367-TIX is a pure acrylic, specially formulated clear drying protective topcoat / sealer with an ultra matt finish for **ACRYFLEX-T** tennis courts and **PAVERCOAT 43 2K** cycle & walking path systems.

Advantages

- Ultra matt finish
- Water repellent
- 0 VOC product
- Easy application
- Perfect scratch resistance
- Thixotropic
- Ready to use
- Fast drying

Position in the system

- **Finishing** — GLOSSCOAT 367-TIX — THIS PRODUCT
- **Colour coat** — PRECOAT 367-200 range
- **Cushion layers** — UNIRUBBER range
- **Resurfacer** — ACRYLIC RESURFACER 367-30 · LW · 367-43
- **Primer** — ACRYLIC PRIMER 367-28 · AQ PRIMER 2K
- **Sub-base** — Asphalt / concrete

ACRYFLEX-T

Cushioned acrylic tennis court system

ITF classified system surfaces

Technical data (at +20 °C)

Colour	**Clear drying**	Overcoating interval	**minimum 2 h**
Mass density (approx.)	**0.93 g/cm³**	Theoretical consumption	**0.150–0.200 kg/m² (1 layer)**
Solids content (by weight)	**39 %**	Application temperature	**+14 °C to +35 °C**
Touch dry	**30 min**	Shelf life	**12 months**

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Application procedure

01

Surface preparation

Clean the surface of grease, salts, debris, dust and any other contaminants.

02

Application

Ready to use – no special procedure. Apply with roller, brush or spray onto any acrylic sport flooring topcoat.

Application conditions

+14 °C – +35 °C

Do not apply the material at temperatures below +14 °C or above +35 °C.

Consumption

0.150–0.200 kg/m²

Theoretical consumption for 1 layer, depending on surface porosity.

Important: coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Packaging

- 50 kg polyethylene drums
- 180 kg steel drums

Storage

- Store in sealed drums in an indoor, dry warehouse at +15 °C to +35 °C.
- Shelf life: 12 months from the production date in a cool, dry place.
- Do not leave the product outdoors exposed to the sun.

Safety

- Not classified as hazardous.
- Contains no formaldehyde, asbestos, mercury, lead, chromate or their derivatives.
- For safe handling and occupational health & safety see the Safety Data Sheet (SDS).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.