ACRYFLEX-T · TENNIS COURT SYSTEM

Precoat
367-200 WOS Neutral

Concentrated pure acrylic latex based neutral topcoat

COLOUR
Neutral
Light brownish · tintable

1.22 g/cm³	48 %	1–1½ h	min. 3 h	0.300 kg/m²
Density (approx.)	Solids content (wt.)	Touch dry	Overcoating interval	Consumption (concentrate)

Product description

PRECOAT 367-200 WOS NEUTRAL is a concentrated, tintable colour topcoat that is applied on the resurfacer or cushion layers of the **ACRYFLEX-T** tennis court system.

Product characteristics

- 100 % concentrated acrylic latex based topcoat for tennis court flooring systems.
- Neutral base – tinted on site with Unica pigment pastes.

Advantages

- Neutral colour – tint with desired colorants
- Lower stock costs
- Easy mixing on site
- Cost-effective

Position in the system

- **Finishing** — OVERLINE 367-F lines · GLOSSCOAT sealer
- **Colour coat** — PRECOAT 367-200 WOS NEUTRAL — THIS PRODUCT
- **Cushion layers** — UNIRUBBER range
- **Resurfacer** — ACRYLIC RESURFACER 367-30 · LW · 367-43
- **Primer** — ACRYLIC PRIMER 367-28 · AQ PRIMER 2K
- **Sub-base** — Asphalt / concrete

ACRYFLEX-T
Cushioned acrylic tennis court system

ITF classified system surfaces

Technical data (at +20 °C)

Colour	Light brownish (neutral)	Overcoating interval	minimum 3 h
Mass density (approx.)	1.22 g/cm³	Theoretical consumption	0.300 kg/m² (concentrate, 1 layer)
Solids content (by weight)	48 %	Application temperature	+14 °C to +35 °C
Touch dry	1–1½ h	Shelf life	12 months

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Application procedure

01

Surface preparation

Clean the surface of grease, salts, debris, dust and any other contaminants.

02

Base layer

Apply **PRECOAT 367-200 WOS NEUTRAL** after **ACRYLIC RESURFACER 367-30** / LW or **UNIRUBBER 367-40** / LIGHT.

03

Mixing

Add suitable grade silica sand or quartz, the desired pigment paste and tap water. Mix with a slow-speed mixer until homogeneous.

04

Application

Spread with a rubber blade squeegee in 2 layers: 0.450 kg/m² per coat.

Mixing ratio (by weight)



- **75 kg** — PRECOAT 367-200 WOS NEUTRAL
- **45 kg** — Silica sand / quartz (0.1–0.3 mm)
- **12 kg*** — Water*
- **5 kg** — Pigment paste**

*The amount of water may vary with ambient temperature. In hot weather up to 5 % more water may be added. **See pigment paste colours below.

Application conditions

+14 °C – +35 °C

Do not apply the material at temperatures below +14 °C or above +35 °C.

Consumption

0.450 kg/m²

Per coat of the mixture. Approx. 0.800–1 kg/m² in 2 layers, depending on surface quality.

Important: coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Pigment paste colours

Unica Red	Terracota Red	Bosphorus Blue	Sky Blue	Grass Green
Moss Green	Stone Grey	Beige	Forest Green	Unica Violet
Deep Blue	Magenta	Unica Blue	Open Blue	Ocean Blue

Tint with Unica pigment pastes. Colour chips are indicative only – please refer to the Unica colour card. Special colours on request.

Packaging

- 75 kg polyethylene drums
- 200 kg steel drums

Storage

- Store in sealed drums in an indoor, dry warehouse at +15 °C to +35 °C.
- Shelf life: 12 months from the production date in a cool, dry place.
- Do not leave the product outdoors exposed to the sun.

Safety

- Not classified as hazardous.
- Contains no formaldehyde, asbestos, mercury, lead, chromate or their derivatives.
- Contains fire-retardant additives.
- For safe handling and occupational health & safety see the Safety Data Sheet (SDS).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.