PRIMERS · BONDING PRIMER

L'unicbond Ultra

Bonding primer for non-porous siliceous, glass and metal surfaces

30–40 ml/m²	25–40 m²/l	approx. 1 h	min. +15 °C	Solvent-free
Consumption	Yield	Drying (20 °C, 50 % RH)	Floor & material temp.	Does not form a film

Product description

L'UNICBOND ULTRA is a bonding primer formulated for non-porous siliceous substrates such as ceramic tiles and polished stone, as well as glass and metal. It is recommended before applying UNICA PUD, PU and epoxy coatings.

Product use

- Granite
- Acrylic tiles
- Glazed ceramic tiles
- Glass and metal substrates
- Before UNICA PUD, PU and epoxy coatings

Advantages

- Solvent-free
- User-friendly application
- Does not form a film
- Activates non-porous surfaces

Position in the system

Coating
UNICA PUD · PU · epoxy system

Bonding primer — THIS PRODUCT
L'UNICBOND ULTRA · 30–40 ml/m²

Substrate
Ceramic tiles · polished stone · glass · metal

Renovation over tiles

Adhesion bridge on non-porous surfaces

Technical data (at +20 °C)

Consumption	approx. 30–40 ml/m²	Film formation	None
Yield	approx. 25–40 m²/l	Solvent content	Solvent-free
Walkable / next step	after approx. 1 h (20 °C, 50 % RH)	Shelf life	6 months
Min. floor & material temperature	+15 °C		

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Application procedure

01

Surface preparation

Remove all concrete remnants, curing agents, loose particles, dirt and organic residues (varnish, care products, oils, wax).

02

Cleaning

Clean thoroughly and rinse with clear water – a 150 rpm monodisc machine with a PU renovation pad is recommended.

03

Application

Apply a thin, even layer with a clean polish applicator, mop or roller so the whole area is uniformly wetted with a closed film.

04

Coating

After approx. 1 h check that drying is complete (also in joints) and coat immediately – long intervals reduce surface activation.

Consumption
30–40 ml/m²
Yield approx. 25–40 m²/l.

Temperature
min. +15 °C
Floor and material during application and drying.

Drying
approx. 1 h
At 20 °C, 50 % RH with ventilation – longer when cold, humid or poorly ventilated.

Important: coat immediately after drying – an extended interval between drying and sealing can reduce surface activation.

Packaging

- 5 kg polyethylene bottles

Storage

- Store sealed indoors in dry areas at +15…+35 °C.
- Do not leave outdoors exposed to the sun.
- Shelf life: 6 months from production.

Safety

- Not hazardous; contains no formaldehyde, asbestos, mercury, lead or chromate.
- Contains fire-retardant additives.
- See the Safety Data Sheet (MSDS).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

unica | Boytem

BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com