l'unicflex™ | ATHLETICS TRACKS · POLYURETHANE

PU 901 Sealer 2K

Elastic polyurethane pore-filling coating for poured SBR floors

COLOURS

Oxide red · Blue

thixotropic pore filler

1.27 g/cm³	99 %	20–25 min	4–5 h	1.3–1.5 kg/m²
Mixed density (20 °C)	Solids (by weight)	Pot life (20 °C)	Touch dry (20 °C)	Consumption

Product description

PU 901 SEALER 2K is an elastic, two-component, thixotropic, solvent-free polyurethane coating for levelling and sealing the pores of poured SBR surfaces in tartan athletics tracks and similar sports systems. It is the pore-filling layer of the **L'UNICFLEX MULTI** athletics system.

Uses

- Pore sealing of poured SBR athletics tracks
- Full polyurethane sports systems
- Multi-purpose SBR and EPDM surfaces
- Basketball, volleyball and handball surfaces, fitness floors
- School indoor play areas and game rooms
- Repair and renovation of existing PU sports floors

Advantages

- Solvent-free
- High elasticity, durability and tear resistance
- High moisture resistance, optimum curing time
- Can be applied in all weather conditions
- Designed for outdoor durability
- Easy to apply

Position in the system

- **Line marking** — UNIPU OVERLINE 2K
- **UV topcoat (optional)** — PU TOPCOAT WB 1K · 0.30 kg/m²
- **EPDM granules** — Coloured EPDM 1–3.5 mm broadcast
- **Elastic layer** — UNIPU 901 2K · 2.2 kg/m²
- **Pore filler** — PU 901 SEALER 2K · 1.3 kg/m² — THIS PRODUCT
- **SBR base layer** — SBR 1–4 mm + UNIPU 030 1K · approx. 10 mm
- **Primer** — UNIPU 045 1K (concrete) · UNIPU 060 1K (asphalt)
- **Substrate** — Concrete / asphalt (min. 30 days, moisture ≤ 3 %)

L'unicflex MULTI

PU sandwich system for athletics tracks

EN 14808 · EN 14809 · EN 13036-4

Athletics surfaces · test report available

Also part of the L'unicflex PRO full-PU athletics track system.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

System performance · DIN 18035-6

Results of the L'unicflex MULTI sandwich athletics system (SBR base + **PU 901 SEALER 2K** + **UNIPU 901 2K** + EPDM), documented by accredited laboratories in England.

38 %	2.2 mm	0.59 N/mm²	66 %	77
Force reduction	Vertical deformation	Tensile strength	Elongation at break	Slip resistance (wet)

Water permeability: impermeable · Flammability: DIN 51960 Class 1. Athletics test report available upon request.

Technical data (at +20 °C)

Component A	**PU resin (coloured)**	Touch dry (20 °C)	**4–5 h**
Component B	**Hardener**	Full dry (20 °C)	**24 h**
Colour	**Oxide red, blue**	Full cure	**7 days**
Mixed density (20 °C)	**1.27 g/cm³**	Elongation	**61 %**
Solids (by weight)	**99 %**	Shore hardness (28 days)	**A 80 · D 48**
Application temperature	**+10 °C to +30 °C**	Consumption	**1.3–1.5 kg/m²**
Pot life (20 °C)	**20–25 min**	Recoat interval	**min. 16 h – max. 24 h**

Chemical resistance

Diluted acids · Diluted & concentrated alkalis · Cleaning detergents · Disinfectants · Vegetable, mineral & animal oils · Fresh & salt water · Diesel & gasoline · Alcohol · Many other solvents

Application procedure

01 — Surface preparation
Apply after the SBR layer is complete – no primer needed. The surface must be dry, clean and free of dust and oil.

02 — Mixing
Condition kits to +15…+25 °C. Mix component A 3–4 min at 300–400 rpm, add B, transfer to a clean container, mix 1–2 min and rest 1–2 min.

03 — Application
Fill the pores with a flat steel trowel to the desired thickness.

04 — Recoating
Recoat within min. 16 h – max. 24 h. If exceeded, sand the surface for good adhesion.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Mixing ratio (by weight)

88 parts	12 parts

88 parts
Component A – PU resin (coloured)

12 parts
Component B – hardener

Supplied as ready-to-use kits (17.6 kg A + 2.4 kg B). Never add thinners.

Application conditions
+10 °C – +30 °C
Ambient and surface temperature. Avoid extreme heat, rain and wind.

Consumption
1.3–1.5 kg/m²
Depending on thickness and floor conditions. Varies with the selected system.

Pot life
20–25 min
At +20 °C. Do not prepare more material than can be applied within the pot life.

Important: protect the finished coating from water contact for at least 24 hours. Immediate water contact causes a sticky film that must be removed and re-applied.

Points to consider

- Bring materials to site 1–2 days before use; in cold weather heat the area and condition packs at +20/+25 °C.
- Use a mechanical mixer (300–400 rpm) with a PU mixing paddle – avoid hand mixing. Never add thinners.
- Transfer the mix to a clean container – unmixed A or B components will not cure.
- Low temperatures extend pot life and curing times and increase consumption; high temperatures shorten them.
- Where day/night temperature differences are extreme, start early and finish on the same day.
- Two-component PU systems must be applied by professional, experienced teams.

Packaging

- Kit: 17.6 kg A + 2.4 kg B

Storage

- Store unopened, sealed packs in cool, dry areas.
- Protect from freezing.
- Shelf life: 6 months from production at +15…+25 °C.
- Opened packs: use within 2 weeks after thorough mixing.

Safety

- Not classified as hazardous; contains no formaldehyde, asbestos or mercury.
- Contains flame-retardant additives.
- Wear workwear, goggles, mask and gloves – the hardener can be irritating.
- Apply in well-ventilated areas. See the Safety Data Sheet (SDS).

Cleaning

- Clean tools before the material dries with UP-002 Thinner.
- Cured material can only be removed mechanically (scraping, grinding).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com