l'unicflex™ | INDOOR SPORTS FLOORS · POLYURETHANE

PU Sealer 2K

Elastic polyurethane pore-filling coating for indoor sports surfaces

COLOUR
Grey
thixotropic pore filler

1.27 g/cm³	99 %	20–25 min	4–5 h	61 %
Mixed density (20 °C)	Solids (by weight)	Pot life (20 °C)	Touch dry (20 °C)	Elongation

Product description

PU SEALER 2K is a thixotropic, two-component, solvent-free, elastic polyurethane filling coating for levelling and pore sealing of indoor sports surfaces and rolled or cast SBR. It forms the pore-filling layer of the **L'UNICFLEX PU** indoor system, tested to **BS EN 14904:2006**.

Application areas

- Basketball, volleyball and handball sports surfaces
- Fitness centre floors
- Full polyurethane sports systems
- Multi-purpose SBR and EPDM fields
- School indoor play areas and playrooms
- Repair and renewal of existing PU-coated sports surfaces

Advantages

- Solvent-free
- High elasticity, durability and tear resistance
- High moisture resistance, optimum curing time
- Can be applied in all climatic conditions
- Durable in outdoor conditions
- Easy to apply

Position in the system

Line marking
PU OVERLINE 2K

Matt topcoat
PU FLEX MATT TOPCOAT 2K · 0.20–0.25 kg/m²

Elastic layer
PU ELASTIC SL 2K · 2 × 1.2 kg/m²

Pore filler — THIS PRODUCT
PU SEALER 2K · approx. 0.70 kg/m²

Rubber base
SBR prefabricated roll, bonded with UNIPU 030 2K

Primer
UNEPOX PRIMER 2K · 0.15–0.25 kg/m²

Substrate
Concrete (min. 30 days, moisture ≤ 3 %)

L'unicflex PU indoor

Polyurethane indoor sports floor system

BS EN 14904:2006
Tested system · UK CST accredited laboratory

Also used in the L'unicflex PU GYM indoor and PU PG indoor systems.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

System performance · BS EN 14904:2006

Results of the L'unicflex PU indoor system (rubber base + **PU SEALER 2K** + 2 × **PU ELASTIC SL 2K** + matt topcoat), tested in a UK CST accredited laboratory.

31 %	1.9 mm	99 %	104	No damage
Shock absorption	Vertical deformation	Vertical ball rebound	Friction	Rolling load

The test report can be shared upon request.

Technical data (at +20 °C)

Component A	**Polyurethane resin (coloured)**	Touch dry (20 °C)	**4–5 h**
Component B	**Polyurethane hardener**	Drying time (20 °C)	**24 h**
Colour	**Grey**	Full cure	**7 days**
Mixed density (20 °C)	**1.27 g/cm³**	Elongation	**61 %**
Solids (by weight)	**99 %**	Shore hardness (28 days)	**A 80 · D 48**
Application temperature	**+10 °C to +30 °C**	Recoat interval	**min. 16 h – max. 24 h**
Pot life (20 °C)	**20–25 min**	Shelf life	**6 months**

Chemical resistance

Diluted acids · Diluted & concentrated alkalis · Cleaning detergents · Disinfectants · Vegetable, mineral & animal oils · Fresh & salt water · Diesel & gasoline · Alcohol · Many other solvents

Application procedure

01 — Surface preparation
Apply after the SBR roll installation is complete – no primer needed. The surface must be dry, clean and free of dust and oil.

02 — Mixing
Condition kits to +15…+25 °C. Mix component A 3–4 min at 300–400 rpm, add B, transfer to a clean container, mix 1–2 min and rest 1–2 min.

03 — Application
Draw across the rubber base with a flat steel trowel to fill pores and joints to the desired thickness.

04 — Recoating
Recoat within min. 16 h – max. 24 h. If exceeded, sand the surface for good adhesion.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Mixing ratio (by weight)

88 parts	12 parts

- **88 parts**
  Component A – PU resin (coloured)
- **12 parts**
  Component B – hardener

Supplied as ready-to-use kits (17.6 kg A + 2.4 kg B). Never add thinners.

Application conditions
+10 °C – +30 °C
Ambient and surface temperature. Avoid extreme heat, rain and wind.

Consumption
approx. 0.6–1.4 kg/m²
Depending on thickness and surface; approx. 0.70 kg/m² in the PU indoor system.

Pot life
20–25 min
At +20 °C. Do not prepare more material than can be applied within the pot life.

Important: protect the finished coating from water contact for at least 24 hours. Immediate water contact causes a sticky film that must be removed and re-applied.

Points to consider

- Bring materials to site 1–2 days before use; in cold weather heat the area and condition packs at +20/+25 °C.
- Use a mechanical mixer (300–400 rpm) with a PU mixing paddle – avoid hand mixing. Never add thinners.
- Transfer the mix to a clean container – unmixed A or B components will not cure.
- Low temperatures extend pot life and curing times and increase consumption; high temperatures shorten them.
- Where day/night temperature differences are extreme, start early and finish on the same day.
- Two-component PU systems must be applied by professional, experienced teams.

Packaging

- Kit: 17.6 kg component A + 2.4 kg component B

Storage

- Store unopened, sealed packs in cool, dry areas.
- Protect from freezing.
- Shelf life: 6 months from production at +15…+25 °C.
- Opened packs: use within 2 weeks after thorough mixing.

Safety

- Not classified as hazardous; contains no formaldehyde, asbestos or mercury.
- Contains flame-retardant additives.
- Wear workwear, goggles, mask and gloves – the hardener can be irritating.
- Apply in well-ventilated areas. See the Safety Data Sheet (SDS).

Cleaning

- Clean tools before the material dries with UP-002 Thinner.
- Cured material can only be removed mechanically (scraping, grinding).

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com