unica

l'unicflex™ | PRIMERS · POLYURETHANE

UNIPU 060 1K

Moisture-curing one-component PU primer for asphalt surfaces

0.88 g/cm³	47 %	12 s	9 h	0.150–0.200 kg/m²
Density (23 °C)	Solids content	Viscosity (Ford cup 4)	Recoating time (23 °C)	Consumption

Product description

UNIPU 060 1K is a solvent-based, one-component, moisture-curing polyurethane primer for asphalt surfaces. It is used as an adhesion primer on asphalt sports flooring sub-bases under PU coatings such as **UNIPU 901 2K** or rubber mats.

Principal characteristics

- Good adhesion to smooth surfaces
- Low viscosity – fills surface capillaries
- Reacts with humidity and cures fast
- Resistant to alkalis, weak acids, mineral oils, fuels and lubricants

Advantages

- Ready to use – no thinning
- Easy to apply
- Fast curing
- Excellent mechanical strength

Position in the system

Line marking
UNIPU OVERLINE 2K

UV topcoat (optional)
PU TOPCOAT WB 1K · 0.30 kg/m²

EPDM granules
Coloured EPDM 1–3.5 mm broadcast

Elastic layer
UNIPU 901 2K · 2.2 kg/m²

Pore filler
PU 901 SEALER 2K · 1.3 kg/m²

SBR base layer
SBR 1–4 mm + UNIPU 030 1K · approx. 10 mm

Primer — THIS PRODUCT
UNIPU 060 1K · 0.150–0.200 kg/m²

Substrate
Concrete / asphalt (min. 30 days, moisture ≤ 3 %)

L'unicflex systems

Primer for all outdoor and indoor PU sports systems

Used in L'unicflex MULTI, PRO, INDOOR, SPRAY COAT and 2S. It can also be used in other systems and applications.

Technical data (at +20 °C)

Density (23 °C)	**0.88 g/cm³**	Recoating time 23 °C	**9 h**
Solids content	**47 %**	Recoating time 30 °C	**5 h**
Viscosity (Ford cup 4, 23 °C)	**12 s**	Surface / application temp.	**+10 °C to +40 °C**
NCO content	**8 %**	Applicable rel. humidity	**40–90 %**
Recoating time 10 °C	**12 h**	Consumption	**0.150–0.200 kg/m²**

Application procedure

01

Surface preparation

The substrate must be firm, dry and load-bearing, free of oil, grease, dust and paint. Bond strength min. 1.0 N/mm²; shot-blast or grind if needed. Moisture max. 4 %, surface min. 3 °C above dew point.

02

Application

Ready to use – apply immediately by roller, brush or low-pressure airless. Apply thin, uniform coats: too thick films may foam.

03

Next layer

Lower temperatures slow the reaction and extend recoating time (12 h at 10 °C, 9 h at 23 °C, 5 h at 30 °C).

Application conditions

+10 °C – +40 °C

Surface and application temperature; relative humidity 40–90 %.

Consumption

0.150–0.200 kg/m²

Apply in thin, uniform coats to avoid foaming.

Important: do not dilute with solvent. Do not use alcoholic solvents or water for cleaning.

Packaging

- 180 kg steel drums
- 20 kg cans

Storage

- Store in original closed drums in dry conditions at +5…+25 °C.
- Do not expose drums to direct sunlight.
- Shelf life: at least 12 months under these conditions.

Safety

- Non-hazardous in cured condition.
- For protective measures, transport and waste management, see the SDS.

Cleaning

- Clean re-usable tools with UP-008 Thinner.
- Do not use alcoholic solvents or water.

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

unica | Boytem

BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com