WATERPROOFING · POLYURETHANE

UNIPU 1000 W

One-component polyurethane liquid waterproofing membrane – white

COLOUR
White
1K PU membrane

1.42–1.47 g/cm³	3000–5000 mPa·s	≥ 400 %	≥ 2.4 N/mm²	1.6–1.8 kg/m²
Density	Viscosity (23 °C)	Elongation at break	Adhesion to concrete	Min. total consumption

Product description

UNIPU 1000 W is a one-component, polyurethane-based liquid waterproofing material. Easy to apply and economical, it bonds strongly to all kinds of surfaces and forms a highly elastic film. Its pure elastomeric, hydrophobic polyurethane resin gives excellent chemical, mechanical and thermal resistance.

Application areas

- Gypsum and cement boards; under tiles
- Bathrooms and roofs
- Light roofs of metal or fibre cement
- Asphalt membranes
- Main waterproofing membrane in car parks
- Stadium stands

Advantages

- Excellent mechanical properties
- Non-toxic when cured
- Never softens – max. service 90 °C, shock 200 °C
- Damaged areas are quickly and easily repaired
- Effective chemical resistance
- Breathable – no moisture build-up under the film
- Stays elastic down to -40 °C

Position in the system

Waterproofing membrane — THIS PRODUCT
UNIPU 1000 W · min. 2 coats · 1.6–1.8 kg/m²

Primer (absorbent surfaces)
UNIPU PRIMER 540

Substrate
Concrete ≥ 25 N/mm² · boards · metal · asphalt

Liquid-applied waterproofing
Aromatic one-component PU membrane

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

Technical data (at +20 °C)

Viscosity (23 °C)	**3000–5000 mPa·s (DIN EN ISO 3219)**
Density	**1.42–1.47 g/cm³ (DIN EN ISO 2811)**
Hardness	**Shore A 70**
Water-vapour transmission	**0.8 g/m²·h**
Adhesion to concrete	**≥ 2.4 N/mm²**
Tensile strength (+23 °C)	**> 4 N/mm²**
Elongation at break	**≥ 400 %**

Drying time	**6–8 h**
Recoat interval	**12–24 h**
Full cure	**7 days**
Service temperature	**-40 °C to +90 °C**
Shelf life	**12 months**
Colour	**White**

Application procedure

01

Surface preparation

Sound substrate: compressive strength 25 N/mm², pull-off ≥ 1.5 N/mm². Remove loose concrete, oil, paint and laitance; roughen and vacuum completely – dust in pores causes pinholes.

02

Priming

After substrate analysis, prime absorbent surfaces with **UNIPU PRIMER 540**.

03

Application

Apply by roller or brush in at least two coats of 0.8–0.9 kg/m² each.

04

Recoating

Wait 6–24 h between coats. Full cure after 7 days.

Consumption
1.6–1.8 kg/m²
Minimum total – 0.8–0.9 kg/m² per coat, 2 coats.

Number of coats
min. 2 coats
By roller or brush, 6–24 h between coats.

Service temperature
-40 … +90 °C
Remains elastic at -40 °C; max. shock temperature 200 °C.

Important: dust left in surface pores impairs performance and causes pinholes – vacuum the prepared surface thoroughly before priming.

Packaging

- 5, 20 or 25 kg on request

Storage

- Store in original closed containers in dry conditions at +5…+25 °C.
- Do not expose packs to direct sunlight.
- Shelf life: 12 months under these conditions.

Safety

- Non-toxic when cured.
- Wear suitable protective equipment.
- See the Safety Data Sheet.

Cleaning

- Clean reusable tools before curing with suitable solvents (e.g. butyl or ethyl acetate).
- Never use water or alcoholic solvents on uncured material.

unica | Boytem
BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com

LEGAL NOTE

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved construction practices. UNICA does not make, nor does it authorise any agent or representative to make, any warranty, express or implied, concerning this material, as workmanship, weather, construction, equipment utilised and other variables affecting results are all beyond our control. UNICA warrants only that the material conforms to product specifications, and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNICA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNICA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

unica | Boytem

BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ
Factory: Gümüşova OSB 1. Sk. No:4 İç Kapı No:1 Gümüşova / Düzce – TÜRKİYE
T +90 216 304 03 05 · F +90 216 304 12 15
unicaboya.com · info@unicaboya.com